



EXCELON™ PC

POLYCARBONATE TUBING

CLEAR, STRONG,

IMPACT RESISTANT

For the clarity of glass and the impact resistance of metal, specify Excelon™ PC tubing. Excelon PC provides extraordinary design and fabrication opportunities.

- Made from FDA-approved materials • UL rated • Clear as glass • High tensile strength over wide temperature range • High impact strength — even at low temperatures • Excellent high temperature resistance • Flame-resistant • Self-extinguishing • Can be machined, drilled, cut and sawed • Easily joined with solvents or adhesives²

Excelon PC can be ordered from stock in 1/4" I.D. to 3 3/4" I.D., in 8 ft. lengths. Custom orders are also available in sizes up to 8" O.D. and in a variety of wall thicknesses. Specific formulations are available for tints and colors with performance additives for ultraviolet stabilization, flame retardant (94VO) and radiation resistance.

²Specifications available.

TYPICAL PROPERTIES

PROPERTY	ASTM Method	EXCELON PC			
Specific Gravity	D 792	1.20			
Refractive Index at 25°C	—	1.586			
Rockwell Hardness	D 785	Scale M 73-78 Scale R 112-125			
Abrasion resistance, Taber abraser with CS-17 wheel	D 1044	10 mg/1000 cycles			
Impact strength, notched Izod, 1/8" specimen, ft.-lb./in. of notch	D 256	15-17			
Impact strength, unnotched Izod, 1/8" specimen, ft.-lb./in.	D 256	>60			
Tensile-impact, ft.-lbs./in. ²	D 1822	250			
Tensile-yield strength, psi	D 638	7,000-9,000			
Tensile-ultimate strength, psi	D 638	9,000-11,500			
Tensile modulus, psi	D 638	300,000-345,000			
Elongation	D 638	100-130			
Compressive strength, psi	D 695	12,500			
Compressive modulus, psi	D 695	345,000			
Flexural strength, psi	D 790	12,000-12,700			
Flexural modulus, psi	D 695	320,000-350,000			
Shear-yield strength, psi	D 732	6,000			
Shear-ultimate strength, psi	D 732	10,000			
Light transmission (1/8-inch thick disc)	—	88-90%			
Water-vapor permeability cm ³ /STP/mm/sec./cm ² /cm HG	—	14.0 X 10 ⁻¹³			
Modulus of rigidity, psi	—	116,000			
Deformation under load, 4,000 psi 77°F	D 621	0.2%			
158°F		0.3%			
Water absorption, 24 hour submersion equilibrium 73°F	D 570	0.15% 0.35%			
Heat-deflection temperature °F	D 648	264 psi: 275-285			
Thermal conductivity, cal./sec./cm ² /°C/cm	—	4.6 X 10 ⁻⁴			
Coefficient of linear-thermal expansion, in./in./°F - 30°C to 30°C, in./in./°C	D 696	3.75 X 10 ⁻⁵ 6.6 X 10 ⁻⁵			
Flammability	D 635	Self-extinguishing			
Brittle temperature	D 746	< - 215°C			
Dielectric constant		- 30°C - 3°C 23°C 100°C 125°C			
60 cycles	D 150	3.12 3.14 2.99 3.15 3.13			
10 ⁶ cycles	D 150		2.95		
Power factor					
60 cycles	D 150	0.005 0.0004 0.0009 0.0009 0.0011			
10 ⁶ cycles			0.010		
Volume resistivity, ohm-cm	—	>10 ¹⁷ >10 ¹⁷ 2.1 X 10 ¹⁶ 2.1 X 10 ¹⁵ 2.7 X 10 ¹⁴			
Arc resistance, stainless-steel strip electrodes tungsten electrodes	D 495	10-12 sec 30 sec			
	25°C	100°C			
Dielectric strength, short time	400 v. / mil at 125.0 mils	(The step-by-step values are essentially the same as the short time values for the 125-mil pieces)			

Data shown are average values and should not be used for specifications.

Excelon™ ...Clear Quality



Thermoplastic Processes, Inc.

1268 Valley Road, Stirling, NJ 07980

Tel. 888-554-6400; 908-561-3000 • Fax 800-874-3291; 908-753-6749



LIABILITY CLAUSE

THERMOPLASTIC PROCESSES, INC., hereinafter called the "Manufacturer," warrants that its products shall be free from defects in workmanship and materials. THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EITHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES FOR FITNESS FOR PURPOSE INTENDED. The Manufacturer's liability is limited to the replacement of any materials which, after an examination by the Manufacturer and its sole option, are found to be defective. The Manufacturer will honor only those claims which are presented within ninety (90) days of the delivery of the materials to the purchaser. THE MANUFACTURER SPECIFICALLY DISCLAIMS ANY AND ALL LIABILITY FOR CONSEQUENTIAL DAMAGES. This literature supersedes all previous literature and the responsibilities made thereon.